

DuPont™ Pyralux® FR™ Coverlay

flexible composites

Technical Information

Description

DuPont™ Pyralux® FR™ coverlay is a composite of DuPont™ Kapton® polyimide film, coated on one side with a proprietary, flame retardant B-staged acrylic adhesive. Coverlay can be used to encapsulate etched details in flexible and rigid-flex multi-layer constructions for environmental protection and electrical insulation.

Construction

Coverlay is available in a variety of film and adhesive thicknesses. **Table 1** lists typical constructions.

The product code must be used when ordering coverlay from DuPont.

Packaging

Pyralux® coverlay composites are supplied on 24 inch (610 mm) wide by 250 feet (76 m) long rolls, on nominal 3 inch (76 mm) cores. Narrower widths or cut sheets are also available by special order.

Typical Data

Each manufactured lot, except the four coverlay constructions noted in **Table 1**, is certified to IPC specifications and tested according to IPC Test Method TM-650. See **Table 2**.

Table 1
Coverlay Product Codes

Product Code	Adhesive	Kapton®	IPC
	mil (µm)	mil (µm)	Certification*
FR0110	1 (25)	1 (25)	Yes
FR0120	1 (25)	2 (51)	Yes
FR0130	1 (25)	3 (76)	Yes
FR0150	1 (25)	5 (127)	Yes
FR0210	2 (51)	1 (25)	Yes
FR0220	2 (51)	2 (51)	Yes
FR0230	2 (51)	3 (76)	Yes
FR0250	2 (51)	5 (127)	Yes
FR0310	3 (76)	1 (25)	Yes
FR7001	1/2 (13)	1/2 (13)	Yes
FR7013	1 (25)	1/2 (13)	Yes
FR7082	2 (51)	1/2 (13)	No
FR1510	1/2 (13)	1 (25)	Yes
FR7332	3/4 (19)	1/2 (13)	No

*Certified to IPC-4203/1: "Adhesive Coated Dielectric Films for Use as Cover Sheets for Flexible Printed Circuits."

Table 2: Pyralux® FR™ Coverlay Properties

Property	Typical Coverlay Value	Test Method
Flammability*	VTM-0	UL94
Meets UL796 Direct Support Requirements	Yes	UL796
Peel Strength* After lamination After soldering	— 1.6 N/mm (9 lb/in) 1.6 N/mm (9 lb/in)	IPC-TM-650, No. 2.4.9 Method B Method D
Solder Float Resistance 10 sec at 288°C (550°F)	Pass	IPC-TM-650, No. 2.4.13 Method B
Adhesive Flow, µm/µm (mil/mil)	4.0	IPC-TM-650, No. 2.3.17.1
Thickness Tolerance	±10%	IPC-TM-650, No. 4.6.2
Dimensional Stability	-0.03%	IPC-TM-650, No. 2.2.4 Method A
Dielectric Constant (at 1 MHz)	3.5	IPC-TM-650, No. 2.5.5.3
Dissipation Factor (at 1 MHz)	0.02	IPC-TM-650, No. 2.5.5.3
Dielectric Strength	137 kV/mm (3500 V/mil)	ASTM D-149
Insulation Resistance (at ambient)	10 ⁶ megohms	IPC-TM-650, No. 2.6.3.2
Volume Resistivity (at ambient)	10 ⁹ megohm-cm	ASTM D-257
Surface Resistance (at ambient)	10 ⁷ megohms	ASTM D-257

*Laminating Conditions: 14 kg/cm² (200 psi), 182°C (360°F), 1 hour to treated side of 1 oz RA copper foil.

A Certificate of Conformance (COC) is available with every batch. Complete material and manufacturing records for each lot, with samples of finished laminate, are retained for reference purpose. The roll labels contain the lot number, DuPont order number, customer order number, IPC specification, customer specification, and customer part number; save these labels for reference in case of inquiries.

Processing

Laminating conditions for DuPont™ Pyralux® flexible composites are typically in the following ranges:

Part Temperature:	182–199°C (360–390°F)
Pressure:	14–28 kg/cm ² (200–400 psi)
Time:	1–2 hours, at temperature

Pyralux® FR™ can be processed like Pyralux® FR™. Refer to publication “Pyralux® Flexible Composites Technical Manual” for further processing details.

Storage Conditions and Warranty

Pyralux® FR™ flexible laminates should be stored in the original packaging at temperatures of 4–29°C (40–85°F) and below 70% humidity. The product should not be frozen and should be kept dry, clean and well protected. Subject to compliance with the foregoing handling and storage recommendations, DuPont’s warranties as provided in the DuPont Standard Conditions of Sale shall remain in effect for a period of two years following the date of shipment.

Safe Handling

Pyralux® FR™ coverlay, sheet adhesive, and bond ply contain a B-staged adhesive. Since B-staged adhesive contains trace quantities (parts per million) of unreacted monomers, operators should take care to minimize contact.

Pyralux® FR™ copper-clad laminates contain fully cured (C-staged) adhesive.



Although DuPont is not aware of anyone developing contact dermatitis when using Pyralux® FR™ products, some individuals may be more sensitive than others. Anyone handling Pyralux® FR™ copper-clad laminates should wash their hands with soap before eating, smoking, or using restroom facilities. Gloves, finger cots, and finger pads should be changed daily. Clothes should be washed frequently.

The unreacted acrylic monomer in the adhesive may impart a mild odor when the release film or paper is removed. We recommend that areas where B-staged materials are used, as well as lay-up and lamination areas, be well ventilated with a fresh air supply.

Pyralux® adhesive is cured during lamination. The curing reaction does not produce any vapors, although impurities may volatilize. When drilling or routing parts made with Pyralux® FR™ flexible composites, provide adequate vacuum around the drill head to minimize worker exposure to adhesive dust.

Thin copper-clad laminates can have sharp metal edges. People handling these materials should be cautioned and provided with suitable gloves to prevent cuts.

Pyralux® FR™ flexible composites DO NOT contain polybrominated biphenyls (PBBs), polybrominated biphenyl oxides (PBBOs), or polybrominated diphenyl ethers (PBDEs).



For more information on DuPont™ Pyralux® flexible circuit materials , please contact your local representative, or visit our website:

Americas

DuPont Electronic Technologies
14 T. W. Alexander Drive
Research Triangle Park, NC 27709
Tel: 800-243-2143

Europe, Middle East & Africa

DuPont de Nemours (Luxembourg) s.à r.l.
Rue Général Patton, Contern
L-2984 Luxembourg
Tel: +352 3666 5654

Japan

DuPont KK
Sanno Park Tower
11-1, Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-6111
Tel: 81-3-5521-8660

Taiwan

DuPont Taiwan Hsinchu Branch.
#2, Li-Hsin 4th Rd., Hsinchu Science Park,
Hsinchu 30078, Taiwan
Tel: 886-3-5793654

India

E.I.DuPont India Limited
1001-1012 “Meadows”, 10th Floor
Sahar Plaza Complex
Andheri-Kurla Road, Andheri
(East)
Mumbai 400 059, India
Tel: 91-22-6751-5000
DID: 91-22-6751-5038
Fax : 91-22-67101937

China

DuPont China Holding Co., Ltd.
Shanghai Branch
Bldg. 11, 399 Keyuan Road
Zhangjiang Hi-Tech Park
Pudong New District
Shanghai 201203, China
Tel: 86-21-38622720

Korea

DuPont Korea Inc.
4/5 Floor, Asia Tower
#726, Yeoksam-dong, Kangnam-ku,
Seoul
135-082 Korea
Tel: 82-2-2222-5224

Singapore

DuPont Singapore Pte, Ltd.
1 HarbourFront Place #11-01
HarbourFront Tower One
Singapore 098633
Tel: 65-6586-3091

pyralux.dupont.com

Copyright ©2011 DuPont or its affiliates. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Pyralux® and Kapton® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see “DuPont Medical Caution Statement,” H-50102.

This information is based on data believed to be reliable, but DuPont makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed herein falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. Because DuPont cannot anticipate or control the many different conditions under which this information and/or product may be used, it does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the product for their particular purposes.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patent.

H-73234-4 07/11



The miracles of science™